


YACHTS

PROFESSIONALS





ATTENTION, products announced by  are subject to legislation and can be applied only by informed professionals.



DATA N°01

APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> • 2 to 3 crossed coats of 35 to 40 dry microns • Theoretical spreading rate : 4,9 to 4,3 Sq.m/L for 70 to 80 dry microns 	<p>PU 360</p>	<p>FLEXIBLE POLYURETHANE ACRYLIC VARNISH G → TOPCOAT CLEAR PU 360 UVR OPTION</p>
<ul style="list-style-type: none"> • 2 to 3 crossed coats of 35 to 40 dry microns • Theoretical spreading rate : 5,3 to 4,6 Sq.m/L for 70 to 80 dry microns (depends on color) 	<p>PU 320</p>	<p>FLEXIBLE POLYURETHANE ACRYLIC LACQUER F → TOPCOAT COLOR PU 320</p>
<ul style="list-style-type: none"> • 1 coat of 25 to 35 µm secs • Theoretical spreading rate : 14,9 Sq.m/L for 35 dry microns 	<p>EPU 221</p>	<p>FLEXIBLE INTERCOAT EPOXY-URETHANE E → INTERFACE EPU 221 if 213 or 215 coat is ready to receive the lacque</p>
<ul style="list-style-type: none"> • 1 coat of 70 to 80 dry microns • Theoretical spreading rate : 6,5 Sq.m/L for 80 dry microns 	<p>PU 228 HB</p>	<p>FLEXIBLE POLYURETHANE FILLER D → PORE FILLER PU 228 HB OPTION If 213 or 215 coat need a primer</p>
<ul style="list-style-type: none"> • 2 crossed coats of 40 dry microns • Theoretical spreading rate : 10,8 Sq.m/L for 40 dry microns 	<p>GP 46</p>	<p>UNIVERSAL PRIMER /UNDERCOAT (single component) C → GP 46</p>
<p>Practical spreading rate : 1U/Sq.m/mm of thickness</p>	<p>COMUSLISS ULIROC</p>	<p>PUTTY FILLER (single component) B¹ → ULIROC > 1 mm or B² → COMUSLISS < 1 mm</p>
<ul style="list-style-type: none"> • First coat of 20 dry microns, dilution 20 to 25 % Theoretical spreading rate : 7,4 to 7,1 Sq.m/L • Second coat of 40 dry microns, dilution 5 à 10 % Theoretical spreading rate: 8,4 to 8,1 Sq.m/L 	<p>MP 40</p>	<p>ANTICORROSIVE PRIMER WITH RED LEAD (single component) A → MP 40</p>   <p>T+ - Très toxique</p>
<ul style="list-style-type: none"> • First coat of 20 dry microns, dilution 20 to 25 % Theoretical spreading rate : 7,4 to 7,1 Sq.m/L • Second coat of 40 dry microns, dilution 5 à 10 % Theoretical spreading rate: 8,4 to 8,1 Sq.m/L 	<p>MP 40</p>	<p>ANTICORROSIVE PRIMER WITH RED LEAD (single component) A → MP 40</p>   <p>T+ - Très toxique</p>
<ul style="list-style-type: none"> • 2 coats of 200 dry microns • Theoretical spreading rate : 3 Sq.m/L for 200 dry microns 	<p>BT 51</p>	<p>UNDERCOAT (single component) B → MONOTAR BT 51</p>
<ul style="list-style-type: none"> • 1 coat of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 	<p>MPO 500</p>	<p>INTERCOAT VYNILIC PITCH (single component) C → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> • 2 to 3 coats of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 		<p>ANTIFOULING D → GYPTIS : hard matrix antifouling paint PROTIS : ablative matrix antifouling paint</p>

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL