

YACHTS

DATA N°05



APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> <li>• 2 to 3 crossed coats of 35 to 40 dry microns</li> <li>• Theoretical spreading rate : 4,9 to 4,3 Sq.m/L for 70 to 80 dry microns</li> </ul>		<p>FLEXIBLE ACRYLIC POLYURETHANE VARNISH            H → TOPCOAT CLEAR PU 360 UVR <b>OPTION</b></p>
<ul style="list-style-type: none"> <li>• 2 crossed coats of 35 to 40 dry microns</li> <li>• Theoretical spreading rate : 5,3 to 4,6 Sq.m/L for 70 to 80 dry microns (depends color)</li> </ul>		<p>FLEXIBLE ACRYLIC POLYURETHANE LACQUER            G → TOPCOAT COLOR PU 320</p>
<ul style="list-style-type: none"> <li>• 1 coat of 25 dry microns</li> <li>• Theoretical spreading rate : 20,8 Sq.m/L for 25 dry microns</li> </ul>	EPU 221	<p>FLEXIBLE INTERCOAT EPOXY-URETHANE            F → INTERFACE EPU 221            if 213 or 215 coat is ready to receive the lacque</p>
<ul style="list-style-type: none"> <li>• 1 coat of 70 to 80 dry microns</li> <li>• Theoretical spreading rate : 6,5 Sq.m/L for 80 dry microns</li> </ul>	PU 228 HB	<p>FLEXIBLE POLYURETHANE FILLER            E → PORE FILLER PU 228 HB <b>OPTION</b>            If 213 or 215 coat need a primer</p>
<ul style="list-style-type: none"> <li>• 2 coats of 120 dry microns</li> <li>• Theoretical spreading rate :            EP 213 HB = 4,8 Sq.m/L for 120 dry microns            EP 215 HB = 4,2 Sq.m/L for 120 dry microns</li> </ul>	EP 213 or 215 HB	<p>UNDERCOAT EPOXY PAINT            D → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 2 crossed coats of 250 to 300 dry microns</li> <li>• Theoretical spreading rate : 3,2 Sq.m/L for 300 dry microns</li> </ul>	SP 500	<p>FINISHING EPOXY FILLER            C → SPRAYABLE FILLER 500</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>	100 300	<p>SOLVENT FREE EPOXY FILLER            B → MIX FILL 100 and/or MIX FILL 300</p>
<ul style="list-style-type: none"> <li>• 3 coats of 70 to 80 dry microns</li> <li>• Theoretical spreading rate : 6 Sq.m/L for 75 dry microns</li> </ul>	WI 120	<p>SOLVENT CLEAR EPOXY SYSTEM            A<sup>1</sup> → WOOD IMPREG 120            or            A<sup>2</sup> → Solvent free epoxy stratification</p>
<ul style="list-style-type: none"> <li>• 3 coats of 70 to 80 dry microns</li> <li>• Theoretical spreading rate : 6 Sq.m/L for 75 dry microns</li> </ul>	WI 120	<p>SOLVENT CLEAR EPOXY SYSTEM            A<sup>1</sup> → WOOD IMPREG 120            or            A<sup>2</sup> → Solvent free epoxy stratification</p>
<ul style="list-style-type: none"> <li>• 1 coat of 300 dry microns</li> <li>• Theoretical spreading rate : 3,3 Sq.m/L for 300 dry microns</li> </ul>	455	<p>UNDERCOAT EPOXY PAINT            B → EPOXYGUARD 455</p>
<ul style="list-style-type: none"> <li>• 1 coat of 100 dry microns</li> <li>• Theoretical spreading rate :            EP 213 HB = 5,7 Sq.m/L for 100 dry microns            EP 215 HB = 5 Sq.m/L for 100 dry microns</li> </ul>	EP 213 or 215 HB	<p>UNDERCOAT EPOXY PAINT            C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 1 coat of 75 dry microns</li> <li>• Theoretical spreading rate : 5 Sq.m/L for 75 dry microns</li> </ul>	MPO 500	<p>INTERCOAT VYNILIC PITCH (single component)            D → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> <li>• 2 to 3 coats of 75 dry microns</li> <li>• Theoretical spreading rate : 5 Sq.m/L for 75 dry microns</li> </ul>		<p>ANTI FOULING            E → GYPTIS : hard matrix antifouling paint            PROTIS : ablative matrix antifouling paint</p>

\* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL