



**PLEASURE BOATS  
WITHOUT FILLER**



**APPLICATIONS**

**PRODUCTS**

<p>PU 320 or PU 99 or PU 77</p> <ul style="list-style-type: none"> <li>• 2 to 3 crossed coats of 40 dry microns</li> <li>• Theoretical spreading rate :</li> <li>PU 320 = 4,6 Sq.m/L for 80 dry microns (depends on color)</li> <li>PU 99 = 6,6 Sq.m/L for 80 dry microns (depends on color)</li> <li>PU 77 = 6,5 Sq.m/L for 80 dry microns (depends on color)</li> </ul>	<p>PU 230 or PU 99 or PU 77</p>	<p><b>FLEXIBLE POLYURETHANE ACRYLIC LACQUER</b> E<sup>1</sup> → TOPCOAT COLOR PU 320 or <b>POLYESTER-POLYURETHANE LACQUER</b> E<sup>2</sup> → POLYTOP PU 99 or <b>ACRYLIC-POLYURETHANE LACQUER</b> E<sup>3</sup> → POLYTOP PU 77</p>
<ul style="list-style-type: none"> <li>• 1 coat of 25 to 35 dry microns</li> <li>• Theoretical spreading rate : 14,9 Sq.m/L for 35 dry microns</li> </ul>	<p>EPU 221</p>	<p><b>FLEXIBLE INTERCOAT EPOXY-URETHANE</b> D → INTERFACE EPU 221</p>
<ul style="list-style-type: none"> <li>• 2 coats of 120 dry microns</li> <li>• Theoretical spreading rate :</li> <li>EP 213 HB = 4,8 Sq.m/L for 120 dry microns</li> <li>EP 215 HB = 4,2 Sq.m/L for 120 dry microns</li> </ul>	<p>EP 213 or 215 HB</p>	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 1 coat of 60 dry microns</li> <li>• Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns</li> </ul>	<p>EP 211</p>	<p><b>PRIMAIRE EPOXY ANTICORROSION</b> B → EPOXY PRIMER EP 211</p>
<p>Metal cleaner treatment : spraying/rinsing/drying</p>	<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>	<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>
<p>Metal cleaner treatment : spraying/rinsing/drying</p>	<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>	<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>
<ul style="list-style-type: none"> <li>• 1 coat of 60 dry microns</li> <li>• Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns</li> </ul>	<p>EP 211</p>	<p><b>PRIMAIRE EPOXY ANTICORROSION</b> B → EPOXY PRIMER EP 211</p>
<ul style="list-style-type: none"> <li>• 3 coats of 120 dry microns</li> <li>• Theoretical spreading rate :</li> <li>EP 213 HB = 4,8 Sq.m/L for 120 dry microns</li> <li>EP 215 HB = 4,2 Sq.m/L for 120 dry microns</li> </ul>	<p>EP 213 or 215 HB</p>	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 1 coat of 75 dry microns</li> <li>• Theoretical spreading rate : 5 Sq.m/L for 75 dry microns</li> </ul>	<p>MPO 500</p>	<p><b>INTERCOAT VYNILIC PITCH [single component]</b> D → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> <li>• 2 to 3 coats of 75 dry microns</li> <li>• Theoretical spreading rate : 5 Sq.m/L for 75 dry microns</li> </ul>	<p>E → ISIS : ablative matrix antifouling paint</p>	<p><b>ANTIFOULING</b> E → ISIS : ablative matrix antifouling paint</p>

\* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL