



RECOMMENDED SYSTEMS

**CARBON SPARS
VARNISH SYSTEMS**

YACHTS

PU SYSTEMS

DATA

N°45



APPLICATIONS

PRODUCTS

- 4 to 5 crossed coats of 80 to 110 wet microns to obtain a film thickness total of 150 to 180 dry microns
- Theoretical spreading rate : 8,6 Sq.m/L for 40 dry microns (110 wet microns)

FLEXIBLE ACRYLIC POLYURETHANE VARNISH
C → TOPCOAT CLEAR PU 360 UVR

PU 360

B → SANDING WITH ORBITAL WITH GRIT 320/400

- 1 or several coats of 150 to 200 dry microns
- Theoretical spreading rate : 8 Sq.m/L for 200 dry microns (280 wet microns)

PRIMER
HIGH BUILD CLEAR FLEXIBLE POLYURETHANE WITH FAST DRY TIME
B → PORE FILLER PU 220 HB - CLEAR

220 HB -CLEAR

Spats

Complete porosity
Application with rag
Then wip the surface.

CARBONE PORE FILLER

FILLER
SINGLE COMPONENT SYSTEM WITH CARBON POWDER WITH FAST DRY TIME
A → CARBONE PORE FILLER

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL