

UNDERCOAT EP 215 HB

EPOXY POLYAMINO-AMIDE TWO COMPONENT COATING.
High build intercoat or finishing.
Can be applied with high thickness

PRIMER
Two component

Edition September 14

FEATURES

UNDERCOAT EP 215 HB Can be applied with high thickness.

UNDERCOAT EP 215 HB ensure an excellent protection and insulation of epoxy under and above the waterline.

Excellent chemical and physical properties.

Excellent resistance :

- to dry heat
- in immersion
- to solvents

Good spreading rate

Easy to sand

UNDERCOAT EP 215 HB can be applied in 2 crossed coats wet on wet.

RECOMMENDED USES

Bonding primer on :

- gelcoat polyester, vynilester, epoxy
- all composites

Application :

- 2 or 3 coats as sandable filler
- on composite and filler insulation
- on microporous gelcoats
- chemical reinforcement of primers
- good antifouling intercoat (if compatibility with epoxy)
- recoat by itself , no sanding required

UNDERCOAT EP 215 HB is compatible with primer EP 211, EP 140, systems EPOXYGUARD 455, EPOXYGUARD IM 409? Epoxy filler MIX FILL , SPRAYABLE FILLER 500, systems EP 213 HB, EP 200 and accept systems PU 228, EPU 221, PU 77, PU 99 and TOPCOAT COLOR 320.

SPECIFICATION DATA

COATING TYPE: Epoxy polyamide undercoat-

COLOR : White

GLOSS: Semi-gloss

COMPONENT: Two component

○

COMPONENT RATIO :

- Weight : 100 Base / 15 Hardener
- Volume : 4 Base / 1 Hardener

INDUCTION TIME (at 20°C) :

15 minutes with standard hardener
10 minutes with fast hardener

POT LIFE (à 20°C) :

6 hours with standard hardener
2 hours with fast hardener

THINNER: EP N° 3

DENSITY AT 23°C : 1,46 approx.

VOLUME SOLIDS : 51 +/-3 %

VOC : 424 g/l

THEORETICAL SPREADING RATE :

5 Sq.m/L at 100 dry microns

RECOMMENDED FILM THICKNESS PER COAT :

Dry: 100 à 130 microns

Wet: 175 à 230 microns

DRY TIME (at 23°C – 50 to 60 % HR) :

dustfree: 1 h with standard hardener
30 minutes with fast hardener

to handle: 4 h with standard hardener

1h30 with fast hardener

to sand: 24 h with standard hardener

15h with fast hardener

DRY TIME TO RECOAT (at 23°C – 40 to 60 % HR) :

Minimum: 6 h with standard hardener

3 h with fast hardener

Maximum: 3 months with standard hardener

6 days with fast hardener

MAXIMUM TEMPERATURE RESISTANCE : 100°C

SURFACE PREPARATION

All surfaces to be coated must be free of grease, dust, water marks, moisture and other foreign matter and must be properly primed with a compatible epoxy primer. To insure the best appearance, the primer or undercoat should be smooth and free of any surface defects such as runs, dry spray or heavy orange peel.

UNDERCOAT EP 215 HB must be applied on compatible primer.

UNDERCOAT EP 215 HB is compatible with primers AEROPRIM 140 et WOOD IMPREG 120, and it can be recoated by systems PORE FILLER PU 228 HB, EPU 221, AEROXYGLASS 560, PU 77, PU 99, TOPCOAT COLOR PU 320, before MPO 500 and majority of Antifouling.

For all other types of coating, contact our technical department

MIXING AND THINNING

Before mixing components, mix carefully the base portion first to obtain a smooth, homogeneous condition. After mixing the base portion, add the hardener slowly with continued agitation. After adding the hardener, continue to mix slowly.

After 30 minutes of induction time, it's possible to diluate from 0 to 20 % of EP N°3 (depends on application condition or method). You must check the viscosity.

Spray gun application : check the viscosity every 2 hours. Don't forget to mix after every dilution.

APPLICATIONS

APPLICATION METHOD		THINNER	TIP SIZES	PRESSURE
BRUSH	YES (spot finishing)	0 to 10%	1,5 to 2,2 0,019 to 0,021 mm (30 to 60°)	2 to 5 BARS 250 BARS
ROLLER	YES (medium hair)	0 to 10%		
SPRAY GUN	YES	5 to 20%		
AIRLESS SPRAY	YES	2 to 5%		

CONDITIONS FOR APPLICATION :

Optimum : 20 to 25 °C for 50 to 70 % HR

Limit : 15 to 35°C for 30 to 80 % HR

o

The substrate temperature must be at least 3°C above the dew point to avoid any condensation - consult the conversion table available at Map Yachting.

VISCOSITY : 18 s to 22 s Cup AFNOR n°4

PRECAUTIONS AND SHELF LIFE

See the material safety data sheet and product label for complete safety and precaution requirements

PACKAGING : KIT 2,5 or 5 Liters

CLASS ONU : 1263

SHELF LIFE : 12 months in original unopened cans at + 10 and + 25 °C away from humidity - 9 months in tropical climate

FLASH POINT : **Base and fast hardener** = between 23 to 55°C **Standard hardener** = <+21°C

LABEL : **Base** = Xi : Irritant **Hardener** = F : Highly Flammable **Xi** : Irritant



MAP YACHTING
Zone Athélie IV
296 av. de la Tramontane
13 705 LA CIOTAT Cedex

Tél : + 33 (0)4 42 98 14 50
Fax : + 33 (0)4 42 98 14 51
E-mail : sales@map-yachting.com
Web : www.map-yachting.com

We guarantee our products against hidden defaults over material and preparation. Our Responsibility is limited at the obligation of freely replacing the defective material without there being a claim for any compensation. The advice we give is based on our experience but they might not be absolutely right. Consequently this does not imply our responsibility in case of inefficiency. Even more our company can not be responsible for any material or corporal damages caused due to a misuse or mishandling of our products. All concession to these clauses, to be valid, must be an official document issued by our offices and signed by our direction.